




Bh. 3	
Analyseprøver	Al ₂ O ₃
0.85 - 1.80 m	2.40 "
1.80 - 3.80 "	3.40 "
3.80 - 5.85 "	3.10 "
5.85 - 7.55 "	10.00 "
7.55 - 9.05 "	4.60 "
9.05 - 11.20 "	2.80 "
11.20 - 13.25 "	3.40 "
13.25 - 15.20 "	4.60 "
15.20 - 17.20 "	3.10 "
17.30 - 19.25 "	3.20 "
19.25 - 20.60 "	2.70 "
20.60 - 21.10 "	0.80 "

Bh. 2	
Analyseprøve	Al ₂ O ₃
3.20 - 4.55 m	4.00 %
4.55 - 6.10 "	0.30 "
6.10 - 7.85 "	0.36 "
7.85 - 9.55 "	0.60 "

SiO₂ = 98,6 %
 Al₂O₃ = 0,53 "
 TiO₂ = 0,05 "
 Fe₂O₃ = 0,14 "
 P = 0,007 "

Bh. 1	
Analyseprøver	Al ₂ O ₃
12.35 - 13.10 m	9.20 %
13.10 - 14.70 "	0.85 "
14.70 - 16.70 "	0.25 "
16.70 - 18.65 "	0.63 "
18.65 - 20.65 "	0.76 "
20.65 - 22.45 "	0.55 "
22.45 - 24.30 "	0.38 "
24.30 - 26.50 "	0.36 "
26.50 - 27.10 "	0.20 "

SiO₂ = 98,5 %
 Al₂O₃ = 0,50 "
 TiO₂ = 0,04 "
 Fe₂O₃ = 0,25 "
 P = 0,004 "

BILAG 6
10.mars 1966.

Profil E3

KVARTSITTSON E E
Fauskeidet

M. 1:500

10499

Skorovas 24.1.66/

P4-21-109