




Bh.10

Analysepröve	Al ₂ O ₃
0.00 - 4.00 m	5.20 %
4.95 - 8.40 "	4.60 "
8.40 - 11.00 "	8.40 "
25.50 - 28.00 "	9.00 "

Bh. 4

Analysepröve	Al ₂ O ₃	SiO ₂ = 98,5 %
10.40 - 11.60 m	0.38 %	Al ₂ O ₃ = 0,57 "
12.20 - 15.30 "	0.77 "	TiO ₂ = 0,06 "
46.40 - 48.35 "	8.40 "	Fe ₂ O ₃ = 0,16 "
		P ₂ O ₅ = 0,02 "

Bh. 6

Analysepröve	Al ₂ O ₃	SiO ₂ = 98,6 %
7.00 - 9.00 m	0.80 %	Al ₂ O ₃ = 0,74 "
9.00 - 12.00 "	1.20 "	TiO ₂ = 0,05 "
12.00 - 14.80 "	0.38 "	Fe ₂ O ₃ = 0,08 "
		P ₂ O ₅ = 0,002 "

BILAG 5
10.mars 1966.

Profil E2

KVARTSITTSONE E
Fauskeidet

M. 1:500

Skorovas 24.1.66 / 4

10502

P4-21-109